

## **SH-HT Super Hydrophobic**

Hydrophobic coatings on the market have had the issue that if the contact angle to water is high, the slip-periness and durability of surface goes down and if the slipperiness of the surface is good the contact angle to water and durability goes down. DON COMPANY's SH-HT coating offers excellent contact angle to water as well as excellent durability and a high level of slipperiness to meet the needs of the Optical Industry.

### **Features:**


- 1. Contact angle to water and slipperiness have been improved, compared to other existing hydrophobic coatings, so it is easy to wipe off contamination on the lens surface.
- 2. SH-HT offers durable UV protection without lowering the effectiveness of the hydrophobic properties. Also resists yellowing of the lens.
- 3. Provides excellent impact resistance to the lens surface.

### **Coating method: Desposition**

	Product of A Co.	Existing Product of DON	NEW Product of DON	Product of D co.	Product of E Co.
Contact angle to water(degree)	115	115	117	113	108
Sliding angle(degree)	8	7	5	5	5
Oil pen cleanability(%)	95	95	95	95	95
Oil pen repellent time(sec)	0.5	0.5	0.5	0.7	0.5

<sup>\*</sup> Compare to the existing products or other companies products, the contact angles to water and the slip angle have much improved.


# **SH-HT Super Hydrophobic**



### Test result

	Product of A Co.	Existing Product of DON	NEW Product of DON	Product of D co.	Product of E Co.
Contact angle to water(degree)	107	110	114	104	105
Sliding angle(degree)	13	12	10	15	11
Oil pen cleanability(%)	50	50	50	40	50
Oil pen repellent time(sec)	2	3	2	5	4

## Abrasion resistance



### Test result

	Product of A Co.	Existing Product of DON	NEW Product of DON	Product of D co.	Product of E Co.
Contact angle to water(degree)	103	105	110	100	103
Sliding angle(degree)	15	14	13	17	16
Oil pen cleanability(%)	20	20	20	10	20
Oil pen repellent time(sec)	3	3	2	5	3



Authorized Distributor for THE DON CO, LTD. Korea 11617 Prospect Dr. • Odessa, FL 33556 800-237-8154 • Fax 800-330-3800